

PATENT SPECIFICATION

(11) 1 577 270

1 577 270

- (21) Application No. 2220/78 (22) Filed 19 Jan. 1978
 (31) Convention Application No. 372/77 (32) Filed 19 Jan. 1977 in
 (33) Czechoslovakia (CS)
 (44) Complete Specification Published 22 Oct. 1980
 (51) INT. CL.³ C08F 220/02
 B01D 15/08
 C08F 8/00 //
 C07C 7/12
 (C08F 8/00 8/10 8/12 8/30 8/32 8/34)
 (C08F 220/02 212/36 220/20 220/28 220/32 220/42 220/44)



(52) Index at Acceptance

C3P	203	216	220	222	234	256	302	314	316	FE
B1H	251	252	260	335	350	351	655	660	665	
C2C	1175	200	207	209	20Y	220	221			
	225	226	227	22Y	248	30Y	313	31Y		
	338	339	350	351	353	355	360	361		
	362	363	364	366	367	368	36Y	37X		
	386	410	41Y	43X	54X	561	562	563		
	566	567	568	569	606	607	623	624		
	625	628	633	644	652	655	65Y	662		
	66Y	69Y	73Y	771	776	778	CE	CQ		
	CY	GX	HB	HE	TH	UE	UU	WS	WY	YA
	YD	YK	YN							
C3C	132	368	375	383	385	388	452	454		
C3J	400	406	AJ	CW	DB					
C3W	227	229								
C3Y	B230	F140	F200	F201						
C5E	222	226	232	233	234	CP				

(54) POLAR POLYMERIC SORBENT BASED ON GLYCIDYL ESTERS FOR GAS AND LIQUID CHROMATOGRAPHY

(71) We, ČESKOSLOVENSKÁ AKADEMIE VĚD, a Czechoslovak Corporation, of No. 3 Národní, Praha 1, Czechoslovakia do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:-

10 The invention relates to the polar polymeric sorbent based on glycidyl esters and suitable for gas and liquid chromatography, which enables through its properties the chromatographic separation of mixtures of various compounds.

15 In the early seventies, polymeric sorbents were introduced for application in gas chromatography in connection with advancement in production of macroporous polymers. They are of use, above all, in gas-solid chromatography. Most of the commercially available sorbents of this type are produced on the basis of styrene-divinyl-benzene copolymers. Its substance is, however, close to non-polar anchored phases. This means

that their polarity is relatively low. The polarity measure of anchored phases is expressed in literature, as a rule, in terms of Rohrschneider constants (J.Chromatog.22, 6, 1966); i.e. by O.Oltimes the difference of retention indices of benzene (x), ethanol (y), methyl ethyl ketone (z), nitromethane (u), and pyridine (s) on squalane and the retention indices of these compounds on the given anchored phase. Because relating of retention indices to the anchored phase is not completely correct in the case of gas-solid chromatography, the retention indices on squalane were substituted by the indices of the same standards measured at 150°C on the non-polar sorbent Carbowax B and calculated modified values of Rohrschneider constants were designed x', y', z', u', and s'.

One of the most polar sorbents at present on the market is Porapak T, which has the Rohrschneider constants x' = 1.30, y' = 2.90, z' = 2.21, u' = 3.44 (s' was not determined) and is the homopolymer of ethylene dimethacrylate. The polarity ex-

tent of some polymeric sorbents may be extended by subsequent modification, nevertheless it is too small and the sorbents can be used above all for separation of non-polar compounds.

The application of sorbents based on hydroxyalkyl methacrylate or acrylate gels, according to the Czechoslovak Patent Application No. 159 990, and on their modification products renders broader prospects. These sorbents attain the values of Rohrschneider constants $x' = 2.29$, $y' = 3.53$, $z' = 2.75$, $u' = 4.09$ (s' was not determined). An enhancement of polarity may be also achieved by the ternary copolymerization of polar monomers, such as hydroxyalkyl acrylate or methacrylates, with a non-polar monomer of the alkyl acrylate or methacrylate type and a crosslinking agent, according to the Czechoslovak Patent No. 175 156. The sorbent prepared in this way has Rohrschneider constants $x = 1.73$, $y = 3.24$, $z = 2.63$, $u = 3.95$, and $s = 3.54$.

However, the above mentioned materials do not possess sufficient polarity for separation of some mixtures.

According to the present invention there is provided a polar polymeric sorbent based on glycidyl esters suitable for gas and liquid chromatography, the sorbent including a macroporous copolymer containing 3 - 70 per cent by weight of polymerised monomeric units with epoxy groups selected from glycidyl methacrylate and glycidyl acrylate, the epoxy groups either being unmodified or modified by a nucleophilic agent and 97 - 30 per cent by weight of a cross-linking agent selected from alkylene diacrylate, alkylene dimethacrylate, hydroxy alkylene diacrylate, hydroxyalkylene dimethacrylate, where the alkylene contains 1 - 6 carbon atoms, and divinyl benzene.

Preferably the sorbent also includes up to 30 per cent by weight of polymerised monomeric units with nitrile groups selected from acrylonitrile and methacrylonitrile.

Further types of the polar polymeric sorbent are obtained by the easy modification of epoxy groups with a nucleophilic agent, such as water, carboxylic acids or their derivatives, ammonia, primary and secondary amines, mercapto compounds, and others.

The materials according to the invention are used as packings for columns in gas and liquid chromatography. They are prepared with a broad range of porosity and polarity by a suspension radical polymerization, e.g. according to the Czechoslovak Patent No. 175 112. Their convenient sorption properties are documented by the linear shape of adsorption isotherms and the corresponding peak symmetry of separated compounds. The mechanical and volume stability with changing medium and temperature are ex-

ceptionally good. Also the retention times of compounds separated on the sorbent according to the invention are substantially shorter in comparison with known sorbents and the separations can be generally carried out at lower temperatures.

The invention is further illustrated in examples of performance, without limiting its scope by any means.

Example 1

The sorbent was prepared in a polymerization vessel of 1 litre volume from 600 ml of 1% aqueous solution of polyvinylpyrrolidone and the mixture consisting of 9.6 g of dodecanol, 98.8 g of cyclohexanol, 49.2 g glycidyl methacrylate, 32.8 g of ethylene dimethacrylate, and 0.80 g of 2,2'-azobis(isobutyronitrile). The batch was bubbled through with a stream of nitrogen for 15 minutes, the reactor was then closed and agitation was set off (250 r.p.m.). After five minutes of stirring, the mixture was heated to 70°C. The copolymerization proceeded at this temperature for 2 hours and at 80°C for further 6 hours. After the reaction had been completed, the product was separated and washed by decantation with ethanol (twice), benzene (twice), and again with ethanol (twice).

For chromatographic purposes, the copolymer was extracted with ethanol for 4 hours, dried in a vacuum oven, and fractionated. The fraction of particle size 150-200 μm was used for packing of a glass column 120 cm long and of inner diameter 0.3 cm. The packing was first conditioned at 170°C in a nitrogen stream 20 ml/min. for 24 hours. The values of modified Rohrschneider indices of the sorbent are: $x' = 2.02$, $y' = 3.65$, $z' = 2.96$, $u' = 4.75$, $s' = 3.93$. The separation of 0.2 μl of the mixture of C_7 - C_{12} alkanes was carried out at temperature 175°C and argon through-flow 24 ml/min.

Retention times of individual hydrocarbons were as follows: heptane 1.28 min, octane 1.58 min, nonane 3.15 min, decane 5.15 min, undecane (b.p. 194°C) 8.45 min, dodecane (b.p. 214.5°C) 14.30 min.

Example 2

The separation of 0.15 μl of alcohols on the sorbent according to Example 1 was carried out at temperature 140°C and argon through-flow 25 ml/min. Retention times of individual components: methanol 1.48 min, ethanol 2.64 min, isopropyl alcohol 3.40 min, tert-butanol 4.29 min, propanol 4.96 min, isobutanol 7.98 min, butanol 9.87 min, 3-methyl-butanol (b.p. 132°C) 17.30 min, pentanol (b.p. 137.9°C) 20.00 min.

Example 3

The successful separation of a mixture of methyl to hexyl esters of acetic acid on the

sorbent according to Example 1 was carried out at temperature 175°C and argon through-flow 25 ml/min. Retention times of individual esters: methyl acetate 1.38 min, ethyl acetate 1.93 min, tert-butyl acetate 2.75 min, butyl acetate 4.43 min, pentyl acetate 7.56 min, hexyl acetate (b.p. 169.2°C) 12.21 min.

Example 4

A mixture (0.1 µl) of vinyl hexyl ether, hexanol, cyclohexanol, and 2-methylcyclohexanol was injected into the column packed with the sorbent according to Example 1 at the column temperature 175°C and the through-flow of carrier gas 25 ml/min. The following retention times of individual components are the evidence of successful gas-chromatographic separation: vinyl hexyl ether 5.12 min, hexanol 9.45 min, cyclohexanol 12.48 min, 2-methylcyclohexanol (b.p. 166°C) 15.83 min.

Example 5

A mixture of cyclopentanone, cyclohexanone and 2-methylcyclohexanone was separated under the same conditions as in Example 4. The retention times were: cyclopentanone 6.87 min, cyclohexanone 12.33 min and 2-methylcyclohexanone 14.65 min.

Example 6

A mixture (0.2 µl) of compounds with different functional groups and of very similar boiling points was injected into the column packed with the material according to Example 1 at temperature 115°C and the through-flow of argon 25 ml/min. The retention times of components were as follows: ethanol (b.p. 78.4°C) 5.89 min, 1-chlorobutane (b.p. 77.9°C) 9.32 min, ethyl acetate (b.p. 77.1°C) 11.55 min, methyl ethyl ketone (b.p. 79.6°C) 13.15 min.

Example 7

The copolymer was prepared in the same way as in Example 1 with the distinction that the weights of monomer and crosslinking agent were 24.6 g of glycidyl methacrylate and 57.4 g of ethylene dimethacrylate. The copolymer was extracted, used for packing of a column (120 cm × 0.3 cm), and conditioned in the same way as in Example 1. The relatively lower polarity predeterminates this sorbent above all for separation of compounds which differ in the number of free π -electrons (olefins, cycloolefins, aromatic hydrocarbons), but it can be used also for separation of other types of compounds. The values of modified Rohrschneider constants are as follows: $x' = 1.05$, $y' = 2.37$, $z' = 1.89$, $u' = 2.92$ (s' was not determined). A mixture (0.1 µl) of cyclohexane, cyclohexene and benzene was separated at tempera-

ture 132°C and the through-flow of argon 25 ml/min. Retention of these compounds is affected by the number of free π -electrons in the molecule: cyclohexane (b.p. 80-81°C) 12.33 min, cyclohexene (b.p. 83.3°C) 14.42 min, benzene (b.p. 80.1°C) 18.23 min.

Example 8

Successful separation of 0.1 µl of a mixture of cycloalkanes and equally substituted aromatic hydrocarbons was carried out similarly as in Example 7, at temperature 172°C and the through-flow of argon 25 ml/min. The retention times of individual components were as follows: cyclohexane 5.70 min, benzene 7.91 min, methylcyclohexane 10.23 min, toluene 16.72 min, ethylcyclohexane 22.6 min, ethylbenzene 34.42 min.

Example 9

The sorbent was prepared by the same procedure as in Example 1, with the distinction that the monomer mixture consisted of 32.8 g of glycidyl methacrylate, 16.4 g of acrylonitrile, and 32.8 g of ethylene dimethacrylate. Also the preparation of terpolymer for its chromatographic application, packing of the column which had the same parameters, and conditioning of the packing were carried out in the same way. This sorbent exhibits thermal stability up to 270°C and has a strong polar character. The values of modified Rohrschneider indices are as follows: $x' = 3.62$, $y' = 4.64$, $z' = 4.43$, $u' = 7.00$, $s' = 5.97$. A mixture of 0.2 µl of polar compounds was separated at 108°C and the through-flow of argon 25 ml/min. Individual compounds had the following retention times: diethyl ether 2.76 min, methanol 4.39 min, ethanol 7.14 min, acetone 8.37 min, methyl ethyl ketone 16.90 min.

Example 10

A mixture of carboxylic acids (0.3 µl) was separated on the column packed with the material according to Example 9 at column temperature 170°C and the through-flow of argon 25 ml/min. The retention times were: acetic acid 5.57 min, propionic acid 7.79 min, isobutyric acid 9.02 min, butyric acid 11.45 min, valeric acid (b.p. 187°C) 18.37 min.

Example 11

The copolymer according to Example 1 was modified by hydrolysis and subsequent cyanoethylation in the following way: 50 g of the copolymer was stirred in a threefold volume of 1 N aqueous sulfuric acid and the hydrolysis was carried out at 90°C for 1 hour; 5 g of the hydrolyzed sample was shaken with 15 ml of acrylonitrile and 15 ml of 9 N sodium hydroxide solution at 25°C for 4 hours. The product was then washed with

water until the alkaline reaction ceased and dried in a vacuum oven. The column of 1 m length and 0.35 mm inner diameter was packed with this modified copolymer and conditioned at temperature 180°C in the stream of nitrogen 20 ml/min for hours. This sorbent has also a strongly polar character and application possibilities. The values of modified Rohrschneider constants are as follows: $x' = 2.71$, $y' = 5.14$, $z' = 4.29$, $u' = 7.13$, $s' = 5.81$. A mixture (0.1 μ l) of chlorinated hydrocarbons was separated at the column temperature 150°C, injection temperature 190°C, and through-flow of nitrogen 30 ml/min. The retention times of individual compounds were: 1-chlorobutane 1.10 min, 1,3-dichlorobutane 4.08 min, 1,4-dichlorobutane 7.08 min.

Example 12

A mixture (0.1 μ l) of trichlorobenzenes was separated on the sorbent according to Example 11 at the column temperature 190°C, injection temperature 230°C, and through-flow of nitrogen 30 ml/min. The individual isomers had the following retention times: 1,3,5-trichlorobenzene 3.52 min, 1,2,4-trichlorobenzene 5.21 min, 1,2,3-trichlorobenzene (b.p. 218-219°C) 6.80 min.

Example 13

Separation of C_2 - C_5 carboxylic acids was carried out under the following conditions: the sorbent according to Example 11, column temperature 165°C, injection temperature 220°C, through-flow of nitrogen 30 ml/min, injected volume 0.15 μ l. The retention times obtained: acetic acid 5.20 min, propionic acid 6.74 min, butyric acid 4.19 min, valeric acid 13.90 min.

Example 14

Successful gas-chromatographic separation of a mixture of compounds with different functional groups was carried out on the sorbent according to Example 11 under the following conditions: column temperature 90°C, injection temperature 130°C, injected volume 0.1 μ l, through-flow of nitrogen 30 ml/min. The individual compounds left the column in the following order: 1-chlorobutane 4.36 min, ethanol 6.48 min, butyraldehyde 7.60 min, methyl ethyl ketone 10.70 min.

Example 15

The polymeric sorbent according to Example 1 was modified by heating in a 0.5 N aqueous solution of perchloric acid for 2 hours at 90°C. It was then separated, washed until the acid reaction ceased, extracted with ethanol for 4 hours and dried. For application, it was packed into a column and conditioned. The values of modified Rohrschneider indices are: $x' = 2.93$, $y' =$

5.24, $z' = 4.64$, $u' = 5.52$, s' was not determined. The sorbent was successfully employed for separation of polar compounds by the gas-chromatographic method.

Example 16

The polymer according to Example 1 was heated with a 50 % solution of 2-hydroxyethylamine to 60°C for 6 hours. Then it was washed with water, extracted with ethanol, dried, and packed into a column. The sorbent exhibited the following values of modified Rohrschneider indices: $x' = 3.23$, $y' = 6.12$, $z' = 4.74$, $u' = 6.83$, $s' = 6.53$ and was also successfully used for separation of polar compounds by gas chromatography.

Example 17

The copolymer glycidyl methacrylate - ethylene dimethacrylate was prepared according to Example 1, with the distinction that the monomer mixture consisted of 70 % of glycidyl methacrylate and 30% of ethylene dimethacrylate and that the mixture was agitated during polymerization more vigorously (700 r.p.m.). The fraction of particles with diameter of 15-20 μ m was separated from the resulting product, thoroughly dried and modified in the following way: 5 g of the copolymer was dispersed in 20 ml of stearoyl chloride and shaken at 20°C for 4 hours, at 70°C for 1.5 hours, and at 80°C for 6 hours. The product after stearoylation contained 5.60 % of chlorine. The column 200 \times 8 mm was packed with this sorbent and used for separation of the mixture of aromatic hydrocarbons (benzene, diphenyl, anthracene, chrysene, and benzopyrene) by the method of liquid chromatography. Further sorbents were prepared analogously to Example 1 from the monomer mixtures and under conditions given in the following examples (in Examples 18-24 the monomer mixtures and r.p.m. were distinct).

Example 18

Glycidyl acrylate 24.6 g, 2-hydroxypropylene diacrylate 32.8 g, methacrylonitrile 24.6 g; 300 r.p.m.

Example 19

Glycidyl acrylate 20.5 g, 2,3,4,5-tetrahydroxyhexamethylene dimethacrylate 61.5 g; 1500 r.p.m.

Example 20

Glycidyl methacrylate 49.2 g, 2,3-dihydroxytetramethylene dimethacrylate 32.8 g; 350 r.p.m.

Example 21

Glycidyl methacrylate 8.2 g, tet-

ramethylene diacrylate 73.8 g; 250 r.p.m.

Example 22

Glycidyl methacrylate 16.4 g, divinylbenzene 65.5 g; 1800 r.p.m.

Example 23

Glycidyl methacrylate 2.5 g, ethylene dimethacrylate 79.5 g; 250 r.p.m.

Example 24

Glycidyl methacrylate 41.0 g, ethylene dimethacrylate 32.8 g; acrylonitrile 4.1 g; 250 r.p.m.

Example 25

The copolymer prepared according to Example 1 was modified in the following way: into a vessel equipped with a tight closure, containing 15 g of the copolymer, 10 g of dimethylamine was distilled under intense cooling. The vessel was sealed and its contents were heated to 60°C for 2 hours. After cooling, the vessel was opened, unreacted amine volatilized, and the sorbent, containing 2.23 mmol amino groups per g, was packed into a column. After conditioning in the stream of nitrogen at 180°C, the gas chromatographic separation of mixtures comprising alcohols, hydrocarbons and esters of carboxylic acids was carried out.

Example 26

A sorbent containing SH-groups was prepared from the copolymer formed according to Example 22 (fraction of particle size 5 - 20 μ m) by the procedure described in Example 25, with the distinction that hydrogen sulfide was distilled instead of amine into the reaction vessel. It was packed into a column and used for separation of a mixture of natural compounds by the method of liquid chromatography.

Example 27

The copolymer according to Example 1 (20 g) was placed in a glass flask equipped with a reflux condenser and a stirrer and 50 ml of aqueous ethylene diamine solution (75 % w/w) was added. The mixture was stirred at temperature 80°C for 6 hours, the solid phase was collected on a fritted glass filter and washed with 0.1 N NaOH (1 litre) for 4 hours and with water until the alkaline reaction ceased. After drying, the product was packed into a column, conditioned, and used for the gas-chromatographic separation of a mixture consisting of polar and nonpolar compounds. The sorbent is thermally stable up to 210°C. The values of modified Rohrschneider indices are as follows: $x' = 2.89$, $y' = 6.40$, $u' = 6.98$, $s' = 6.54$.

Example 28

The sorbent containing 2.20 mmol nitrogen/ g was prepared by the analogous procedure as in Example 27 by reaction with methylamine instead of ethylenediamine. It was thermally stable up to 200°C and was employed for the gas-chromatographic separation of mixtures of compounds. The values of modified Rohrschneider indices are as follows: $x' = 2.13$, $y' = 4.67$, $z' = 3.52$, $u' = 4.84$, $s' = 4.80$.

Example 29

The polymer prepared according to Example 17, the fraction of particle size 5-20 μ m, was reacted with dodecylamine by the same procedure as in Example 27 and used as the packing for separation of nonpolar hydrocarbons by the method of liquid chromatography.

Example 30

The polymer prepared according to Example 19 was modified by a similar procedure to that described in Example 27 in which 2-mercaptoethanol is used as the nucleophilic agent. The product was employed for separation of natural compounds by the method of liquid chromatography.

Example 31

The sorbent was prepared by the same procedure as in Example 1, with the distinction that the monomer mixture consisted of 24.8 g of glycidyl methacrylate, 24.6 g of acrylonitrile, and 32.8 g of ethylene dimethacrylate. The product after polymerization was prepared for application by screening, packing of a column and conditioning as in Example 1. A mixture of diols (0.1 μ l) was separated on the column at 195°C and the through-flow of nitrogen 27 ml/min. The retention times of individual components were as follows: 1-butanol 1.25 min, ethylene glycol mono-methacrylate 1.80 min, diethylene glycol diethyl ether 3.66 min, 2,3-butanediol 5.80 min, ethylene glycol 6.50 min, 1,3-propanediol 11.50 min, benzylalcohol 15.76 min.

Example 32

Separation of trichlorobenzene isomers was carried out on the same packing and under the same conditions as in Example 31. The retention times of individual components were as follows: 1,3,5-trichlorobenzene 5.10 min, 1,2,4-trichlorobenzene 6.94 min, 1,2,3-trichlorobenzene 9.66 min.

Example 33

The sorbent prepared according to Example 31, with the distinction that the same amount of methacrylonitrile was used instead of acrylonitrile, was subjected to the

acid hydrolysis of epoxide groups by heating to 80°C in 0.5 M sulfuric acid for 2 hours. The product was washed with water until the acidic reaction ceased and dried. After packing into a column and conditioning, separation of 0.15 µl of a mixture of carboxylic acids was carried out at temperature 170°C and the through-flow of nitrogen 27 ml/min. The retention times of individual components were as follows: acetic acid 7.22 min, propionic acid 10.42 min, valeric acid 27.02 min.

WHAT WE CLAIM IS:

1. A polar polymeric sorbent based on glycidyl esters suitable for gas and liquid chromatography, the sorbent including a macroporous copolymer containing 3 - 70 per cent by weight of polymerised monomeric units with epoxy groups selected from glycidyl methacrylate and glycidyl acrylate, the epoxy groups either being unmodified or modified by a nucleophilic agent and 97 - 30 per cent by weight of a cross-linking agent selected from alkylene diacrylate, alkylene dimethacrylate, hydroxy alkylene diacrylate, hydroxyalkylene dimethacrylate, where the alkylene contains 1 - 6 carbon atoms, and divinyl benzene.

2. A sorbent as claimed in claim 1 wherein the sorbent includes up to 30 per cent by weight of polymerised monomeric units with nitrile groups selected from acrylonitrile and methacrylonitrile.

3. A sorbent as claimed in either claim 1 or claim 2 wherein the nucleophilic agent is selected from water, carboxylic acids and their derivatives, ammonia, primary and second amines, mercapto compounds or acrylonitrile.

4. A polar polymeric sorbent as claimed in any of claims 1 to 3 substantially as hereinbefore described.

5. A polar polymeric sorbent substantially as hereinbefore described with reference to any one of the Examples 1, 7, 9, 11, 15 to 31 and 33.

For the Applicants,
MATTHEWS, HADDAN & CO,
Chartered Patent Agents,
33 Elmfield Road,
Bromley, Kent.

Printed for Her Majesty's Stationery Office,
by Croydon Printing Company Limited, Croydon, Surrey, 1980.
Published by The Patent Office, 25 Southampton Buildings,
London, WC2A 1AY, from which copies may be obtained.